

## Test Report

**UES Co.,Ltd**

Quality Control Department

Contact: Wataru Sugimoto

e-mail: ues@cocowork.com

### Sample

- ① SDGs Granular Carbon Code : **KR-2**
- ② Coconut shell activated carbon Code : KD-GW-A

### Test Item

Comparative test of odorous gas deodorization

### Test Overview

5g of each sample was placed in a 2L polyethylene bag along with gas of a specified concentration.  
After 1 hour, the remaining gas concentration was measured using a detector tube.

### Test Results

Target Gas	Initial Concentration (ppm)	Removal rate after 1 hour	
		<b>KR-2</b>	KD-GW-A
Ammonia	100	Over 99%	95%
Trimethylamine	50	Over 99%	Over 99%
Methyl Mercaptan	20	Over 99%	Over 99%
Hydrogen Sulfide	10	Over 99%	Over 99%

