

## **Test Report**

**UES Co.,Ltd**

Quality Control Department

Contact: Wataru Sugimoto

e-mail: ues@cocowork.com

### **Sample**

Catalyst-Modified Activated Carbon for Aldehyde Removal

Code : **AD**

### **Test Item**

Acetaldehyde gas removal test

### **Test Overview**

The sample (0.2 g) and acetaldehyde (20 ppm) were placed in a 2L plastic bag, and the gas concentration was measured using a detector tube after one hour.

### **Test Results**

Target Gas	Initial Concentration (ppm)	After 1 Hour (ppm)	Removal Rate
Acetaldehyde	20	< 1	Over 99%